



Headquarters  
3001 Maxx Road  
Evansville, IN 47711  
800.209.2517

**TRIVALENCE**

# TriVOL 11T30 (U,R)

trivalancetechnologies.com

## Polypropylene

### General Information

#### Product Description

Homopolymer PP, talc reinforced. melt flow ranges (4-12)

#### FEATURES

-RoHS/REACH Compliant  
-Homopolymer  
-30% Talc Reinforced

- Low Flow

#### ADDITIONAL FORMULAS

-Added Release "R"  
-Added UV "U"

#### COLOR

-All

#### General

**Typical Applications** -Appliance, electrical, lawn & garden, automotive, packaging, industrial  
**Processing Method** -Injection  
**Form(s)** -Pellets  
**Availability** -North America, Europe, Asia, Latin America

### ASTM / ISO Properties<sup>1</sup>

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density	1.13	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (230°C/2.16kg)	8	g/10min	ASTM D1238
Outdoor Suitability (QUV) ("U" grades)	Pass		TVT Internal
<b>Mechanical</b>			
Tensile Strength	5,000	psi	ASTM D638
Tensile Elongation	>6	%	ASTM D638
Flexural Modulus	425,000	psi	ASTM D790
Notched Izod Impact	0.7	ft-lbs/in	ASTM D256
<b>Thermal</b>			
Deflection Temperature Under Load (0.45 MPa)	260	°F	ASTM D648
<b>Flammability</b>			
0.06 in		HB	UL94 TVT Internal
<b>Recommended Processing Guidance</b>			
Drying Temperature	160 to 200	°F	
Drying Time	1 to 3	Hours	
Suggested Max Moisture	0.05	%	
Processing Melt Temperature	410 to 480	°F	
Mold Temperature	80 to 140	°F	

<sup>1</sup> note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.