



**TRIVALENCE**

Headquarters  
3001 Maxx Road  
Evansville, IN 47711  
800.209.2517

# TriEXO 21G40PPS (U,R)

trivalencetechnologies.com

## Polyphenylene Sulfide

### General Information

#### Product Description

High heat resin, PPS, Glass Fiber Reinforced

#### FEATURES

- High Strength
- High Temperature
- Chemical resistant
- 40% Glass Fiber Reinforced
- Medium Flow

#### ADDITIONAL FORMULAS

- Added Release "R"
- Additional UV "U"

#### COLOR

- All

### General

#### Typical Applications

-Appliance, electrical, lawn & garden, automotive, medical, motor housings, oil/gas, military

#### Processing Method

-Injection/Extrusion

#### Form(s)

-Pellets

#### Availability

-North America, Latin America

### ASTM / ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.2mm)	0.3 to 0.5	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, brk	24,500	psi	ASTM D638
Tensile Elongation	>1.5	%	ASTM D638
Flexural Modulus	1,700,000	psi	ASTM D790
Un-Notched Izod Impact	12	ft-lbs/in	ASTM D256
Rockwell Hardness	115	R-Scale	ASTM D785

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	500	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	470	°F	ASTM D648

Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 - TVT Internal

### Recommended Processing Guidance

Drying Temperature	220 to 230	°F
Drying Time	4 to 6	Hours
Suggested Max Moisture	0.02	%
Processing Melt Temperature	600 to 630	°F
Mold Temperature	150 to 300	°F

<sup>1</sup> Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.