



TRIVALENCE

Headquarters
3001 Maxx Road
Evansville, IN 47711
800.209.2517

TriEXO 29G30PEI (U,R)

trivalencetechnologies.com

Polyether Imide

General Information

Product Description

High heat resin, PEI. Glass Fiber Reinforced

FEATURES

- High Strength -30% Glass Fiber Reinforced
- High Temperature
- Chemical resistant
- Inherently Flame Retardant

ADDITIONAL FORMULAS

- Added Release "R"
- Additional UV "U"

COLOR

- All
- Opaque

General

- Typical Applications** -Appliance, electrical, lawn & garden, automotive, medical, motor housings, oil/gas, military
- Processing Method** -Injection/Extrusion
- Form(s)** -Pellets
- Availability** -North America, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cm ³	ASTM D792
Melt Flow Rate (337°C/6.6kg)	5	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.5	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, brk	25,000	psi	ASTM D638
Tensile Elongation	>2	%	ASTM D638
Flexural Modulus	1,350,000	psi	ASTM D790
Un-Notched Izod Impact	10	ft-lbs/in	ASTM D256
Rockwell Hardness	114	R-Scale	ASTM D785

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	418	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	412	°F	ASTM D648
Vicat Softening Temperature	428	°F	ASTM D1525
RTI Elec	350	°F	UL 746
RTI IMP	337	°F	UL 746
RTI Str	350	°F	UL 746
CLTE - Flow	1.1E-5	in/in/°F	ASTM E831

Flammability	Nominal Value	Unit	Test Method
0.06 in	V0/5VA		UL94 - TVT Internal

Recommended Processing Guidance

- Drying Temperature 295 to 305 °F
- Drying Time 4 to 6 Hours
- Suggested Max Moisture 0.02 %
- Processing Melt Temperature 690 to 780 °F
- Mold Temperature 270 to 350 °F

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.