



TRIVALENCE

# TriVALOY 22FR0AM

Polycarbonate + ABS

Headquarters  
3001 Maxx Road  
Evansville, IN 47711  
800.209.2517

trivalencetechnologies.com

## General Information

### Product Description

Non halogenated flame retardant product with antimicrobial additive.

#### FEATURES

- Flame Retardant
- High Impact
- UV Stabilized
- ROHS/REACH Compliant
- Non-halogenated/Non-Brominated/Non-Chlorinated
- Chemical Resistant
- Medium Flow
- Contains Antimicrobial Agent

#### ADDITIONAL FORMULAS

- Added Release
- Additional Melt Flows

#### COLOR

- All
- Opaque/Translucent

### General

- Typical Applications** -Appliance, medical devices
- Processing Method** -Injection
- Form(s)** -Pellets
- Availability** -North America, Europe, Asia, Latin America

## ASTM / ISO Properties<sup>1</sup>

### Physical

	Nominal Value	Unit	Test Method
Density	1.19	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (260°C/5.0kg)	25	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7	%	TVT Internal
Outdoor Suitability (QUV)	Pass		TVT Internal

### Mechanical

	Nominal Value	Unit	Test Method
Tensile Strength, yld	8400	psi	ASTM D638
Tensile Elongation, brk	>60	%	ASTM D638
Flexural Modulus	345000	psi	ASTM D790
Gardner Impact	320	in-lbs	ASTM D5420
Rockwell Hardness	117	R-Scale	ASTM D785

### Thermal

	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	210	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	198	°F	ASTM D648
Vicat Softening Temperature	208	°F	ASTM D1525
RTI Elec	140	°F	UL 746
RTI IMP	140	°F	UL 746
RTI Str	140	°F	UL 746
CLTE - Flow	4.3E-5	in/in/°F	ASTM E831

### Flammability

	Nominal Value	Unit	Test Method
0.06 in	V0		UL94 File E494706
0.10 in	V0, 5VA		UL94 File E494706

### Recommended Processing Guidance

Drying Temperature	165 to 185	°F
Drying Time	3 to 6	Hours
Suggested Max Moisture	0.03	%
Processing Melt Temperature	460 to 500	°F
Mold Temperature	130 to 170	°F

<sup>1</sup> Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.