



TRIVALENCE

Headquarters
3001 Maxx Road
Evansville, IN 47711
800.209.2517

TriVALOY 22G20 - ISO

trivalencetechnologies.com

Polycarbonate + ABS

General Information

Product Description

Glass reinforced polycarbonate + ABS with medium flow and good stiffness.

FEATURES

- Good Heat Resistance
- Good Stiffness
- Medium Impact
- ROHS/REACH Compliant
- 20% Glass Fiber Reinforced

ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"

COLOR

- All
- Opaque

General

Typical Applications

-Automotive, housings

Processing Method

-Injection

Form(s)

-Pellets

Availability

-North America, Europe, Latin America

ASTM / ISO Properties¹

Physical

	Nominal Value	Unit	Test Method
Density	1.2	g/cm ³	ISO 1183
Melt Flow Rate (260°C/5.0kg)	18	g/10min	ISO 1133
Melt Flow Rate (230°C/3.0kg)	3	g/10min	ISO 1133
Molding Shrinkage - Flow (3.2mm)	0.3 to 0.6	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal

Mechanical

	Nominal Value	Unit	Test Method
Tensile Strength, brk	80	MPa	ISO 527
Tensile Elongation, brk	2	%	ISO 527
Flexural Modulus	5400	MPa	ISO 178
Tensile Modulus	6000	MPa	ISO 527
Notched Izod Impact, RT	7.5	kJ/m ²	ISO 179

Thermal

	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	133	°C	ISO 75
Deflection Temperature Under Load (1.8 MPa)	120	°C	ISO 75
Vicat Softening Temperature	130	°C	ISO 306
CLTE - Flow	1.7E-5	in/in/°F	ISO 11359

Flammability

	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 TVT Internal

Recommended Processing Guidance

Drying Temperature	90 to 120	°C
Drying Time	4 to 5	Hours
Suggested Max Moisture	0.02	%
Processing Melt Temperature	240 to 270	°C
Mold Temperature	125 to 170	°C

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.