



TRIVALENCE

TriVALOY 22P

Headquarters
3001 Maxx Road
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

Polycarbonate + ABS

General Information

Product Description

Polycarbonate + ABS with high impact and medium flow. Paintable and Plateable.

FEATURES

- Paintable/Plateable
- High Impact
- Chemical Resistant
- ROHS/REACH Compliant
- Medium Flow

ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"

COLOR

- All
- Opaque/Translucent

General

Typical Applications

-Appliance, lawn & garden, automotive, electronics, medical devices, spools, housings

Processing Method

-Injection

Form(s)

-Pellets

Availability

-North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

Physical

	Nominal Value	Unit	Test Method
Density	1.15	g/cm ³	ISO 1183
Melt Flow Rate (260°C/5.0kg)	18	g/10min	ISO 1133
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7	%	TVT Internal

Mechanical

	Nominal Value	Unit	Test Method
Tensile Strength, yld	55	MPa	ISO 527
Tensile Elongation, brk	120	%	ISO 527
Flexural Modulus	2400	MPa	ISO 178
Gardner Impact	320	in-lbs	ASTM D5420
Charpy Impact (73F)	45	kJ/m ²	ISO 179A
Rockwell Hardness	117	R-Scale	ASTM D785

Thermal

	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	121	°C	ISO 75
Deflection Temperature Under Load (1.8 MPa)	103	°C	ISO 75
Vicat Softening Temperature	122	°C	ISO 306
CLTE - Flow	7.4E-5	cm/cm/°C	ISO 11359

Flammability

	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 TVT Internal

Recommended Processing Guidance

Drying Temperature	95 to 120	°C
Drying Time	2 to 4	Hours
Suggested Max Moisture	0.02	%
Processing Melt Temperature	250 to 290	°C
Mold Temperature	70 to 90	°C

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.