



TRIVALENCE

TriVALOY 32P

Headquarters
3001 Maxx Road
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

Polycarbonate + ABS

General Information

Product Description

Polycarbonate + ABS with high impact and medium flow. Paintable and Plateable.

FEATURES

- Paintable/Plateable
- Great Impact
- Chemical Resistant
- ROHS/REACH Compliant
- High Flow

ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"

COLOR

- All
- Opaque/Translucent

General

Typical Applications

-Appliance, lawn & garden, automotive, electronics, medical devices, spools, housings

Processing Method

-Injection

Form(s)

-Pellets

Availability

-North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

Physical

	Nominal Value	Unit	Test Method
Density	1.15	g/cm ³	ASTM D792
Melt Flow Rate (260°C/5.0kg)	24	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7	%	TVT Internal
Outdoor Suitability (QUV)	Pass		TVT Internal

Mechanical

	Nominal Value	Unit	Test Method
Tensile Strength, yld	7800	psi	ASTM D638
Tensile Elongation, brk	120	%	ASTM D638
Flexural Modulus	340000	psi	ASTM D790
Gardner Impact	320	in-lbs	ASTM D5420
Notched Izod Impact	12	ft-lbs/in	ASTM D256
Rockwell Hardness	117	R-Scale	ASTM D785

Thermal

	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	250	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	218	°F	ASTM D648
Vicat Softening Temperature	248	°F	ASTM D1525
CLTE - Flow	4.4E-5	in/in/°F	ASTM E831

Flammability

	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 TVT Internal

Recommended Processing Guidance

Drying Temperature	180 to 215	°F
Drying Time	2 to 4	Hours
Suggested Max Moisture	0.02	%
Processing Melt Temperature	480 to 540	°F
Mold Temperature	135 to 185	°F

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.