



TRIVALENCE

TriVALOY 32SU

Headquarters
3001 Maxx Road
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

Polycarbonate + ASA

General Information

Product Description

Polycarbonate + ASA with great weatherability.

FEATURES

-Excellent UV Performance
-High Impact
-Chemical Resistant
-ROHS/REACH Compliant
-High Flow

-Weatherable
-High Gloss

ADDITIONAL FORMULAS

-Added Release "R"

COLOR

-All
-Opaque/Translucent

General

Typical Applications

-Appliance, lawn & garden, automotive, electronics, enclosures.

Processing Method

-Injection

Form(s)

-Pellets

Availability

-North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

Physical

	Nominal Value	Unit	Test Method
Density	1.17	g/cm ³	ASTM D792
Melt Flow Rate (260°C/5.0kg)	26	g/10min	ASTM D1238
Melt Flow Rate (220°C/10.0kg)	9	g/10min	ASTM D1239
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7	%	TVT Internal
Outdoor Suitability (QUV)	Pass		TVT Internal

Mechanical

	Nominal Value	Unit	Test Method
Tensile Strength, yld	8000	psi	ASTM D638
Tensile Elongation, brk	50	%	ASTM D638
Flexural Modulus	350000	psi	ASTM D790
Notched Izod Impact	8	ft-lbs/in	ASTM D256
Rockwell Hardness	115	R-Scale	ASTM D785

Thermal

	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa)	230	°F	ASTM D648
Vicat Softening Temperature	246	°F	ASTM D1525
CLTE - Flow	4.0E-5	in/in/°F	ASTM E831

Flammability

	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 TVT Internal

Recommended Processing Guidance

Drying Temperature	190 to 200	°F
Drying Time	3 to 4	Hours
Suggested Max Moisture	0.02	%
Processing Melt Temperature	480 to 520	°F
Mold Temperature	130 to 160	°F

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.