



TRIVALENCE

Headquarters  
3001 Maxx Road  
Evansville, IN 47711  
800.209.2517

# TriVAN 12G15 (U, R, UR)

trivalencetechnologies.com

## Acrylonitrile Butadiene Styrene Glass Fiber Reinforced

### General Information

#### Product Description

Acrylonitrile Butadiene Styrene 15% Glass Fiber reinforced, Impact Modified

#### FEATURES

- Good Impact
- Medium Flow
- Good Stiffness

#### ADDITIONAL FORMULAS

- Added Release "R"
- Additional UV "U"

#### COLOR

- All
- Opaque

### General

#### Typical Applications

-Appliance, construction

#### Processing Method

-Injection/Extrusion

#### Form(s)

-Pellets

#### Availability

-North America, Europe, Latin America

### ASTM / ISO Properties<sup>1</sup>

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density	1.14	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (230°C/3.8kg)	2	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.1 to 0.3	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
<b>Mechanical</b>			
Tensile Strength, yld	10200	psi	ASTM D638
Tensile Elongation	>2.5	%	ASTM D638
Flexural Modulus	660000	psi	ASTM D790
Notched Izod Impact	2	ft-lbs/in	ASTM D256
<b>Thermal</b>			
Deflection Temperature Under Load (0.45 MPa)	218	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	212	°F	ASTM D648
Vicat Softening Temperature	218	°F	ASTM D1525
<b>Flammability</b>			
0.06 in	HB		UL94 - TVT Internal

### Recommended Processing Guidance

Drying Temperature	175 to 200	°F
Drying Time	3 to 5	Hours
Suggested Max Moisture	0.04	%
Processing Melt Temperature	480 to 530	°F
Mold Temperature	110 to 175	°F

1

Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.