



TRIVALENCE

TriVEX 02 (U,R)

Headquarters
3001 Maxx Road
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

Polycarbonate

General Information

Product Description

General purpose, high impact polycarbonate

FEATURES

- High Impact
- High Optical Quality
- Low Flow/Branched Resin

ADDITIONAL FORMULAS

- Added Release "R"
- Additional UV "U"

COLOR

- All
- Transparent

General

- Typical Applications** -Appliance, electrical, lawn & garden, automotive, medical
- Processing Method** -Injection/Extrusion/Blow Molding
- Form(s)** -Pellets
- Availability** -North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ASTM D792
Melt Flow Rate (300°C/1.2kg)	3	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7	%	TVT Internal
Outdoor Suitability (QUV) (12U Grades)	Pass		TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, brk	9500	psi	ASTM D638
Tensile Elongation	>65	%	ASTM D638
Flexural Modulus	330000	psi	ASTM D790
Notched Izod Impact	14	ft-lbs/in	ASTM D256
Rockwell Hardness	118	R-Scale	ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	292	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	266	°F	ASTM D648
Vicat Softening Temperature	302	°F	ASTM D1525
RTI Elec	176	°F	UL 746
RTI IMP	176	°F	UL 746
RTI Str	176	°F	UL 746
CLTE - Flow	3.8E-5	in/in/°F	ASTM E831
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 - TVT Internal

Recommended Processing Guidance

- Drying Temperature 230 to 250 °F
- Drying Time 3 to 6 Hours
- Suggested Max Moisture 0.02 %
- Processing Melt Temperature 600 to 650 °F
- Mold Temperature 175 to 240 °F

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.