



TRIVALENCE

TriVEX 13G30 (U,R)

Headquarters
3001 Maxx Road
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

Polycarbonate

General Information

Product Description

Glass fiber reinforced polycarbonate, impact modified

FEATURES

-30% Glass Fiber Reinforced
-Good Strength -Good Impact
-Good Creep Resistance
-Low Flow

ADDITIONAL FORMULAS

-Added Release "R"
-Added UV "U"

COLOR

-All

General

Typical Applications

-Appliance, electrical, lawn & garden, automotive, electronic

Processing Method

-Injection

Form(s)

-Pellets

Availability

-North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ASTM D792
Melt Flow Rate (300°C/1.2kg)	8	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.4	%	TVT Internal
Outdoor Suitability - QUV ("U" grades only)	Pass		QUV - TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	16,800	psi	ASTM D638
Tensile Elongation	>3	%	ASTM D638
Flexural Modulus	990000	psi	ASTM D790
Notched Izod Impact	3.5	ft-lbs/in	ASTM D256
Rockwell Hardness	121	R-Scale	ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	285	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	275	°F	ASTM D648
Vicat Softening Temperature	290	°F	ASTM D1525
CLTE - Flow	1.7E-5	in/in/°F	ASTM E831
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 TVT Internal
Recommended Processing Guidance			
Drying Temperature	230 to 260	°F	
Drying Time	3 to 6	Hours	
Suggested Max Moisture	0.02	%	
Processing Melt Temperature	560 to 600	°F	
Mold Temperature	175 to 230	°F	

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.