



TRIVALENCE

TriVEX™ 12G20FR0

Headquarters
3001 Maxx Rd
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

Polycarbonate

General Information

Product Description

Flame retardant, 20% glass reinforced polycarbonate

FEATURES

- Flame Retardant
- Good Mechanical Properties
- 20% Glass Fiber Reinforced

ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"

COLOR

- All

General

- Typical Applications** -Appliance, electrical, lawn & garden, automotive, electronic
- Processing Method** -Injection/Extrusion
- Form(s)** -Pellets
- Availability** -North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value Unit	Test Method
Density	1.34 g/cm ³	ASTM D792
Melt Flow Rate (300°C/1.2kg)	8 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.5 %	TVT Internal
Outdoor Suitability QUV ("U" grades only)	Pass	QUV TVT Internal

Mechanical	Nominal Value Unit	Test Method
Tensile Strength, yld	14000 psi	ASTM D638
Tensile Elongation	5 %	ASTM D638
Flexural Modulus	760000 psi	ASTM D790
Notched Izod Impact	1.5 ft-lbs/in	ASTM D256
Rockwell Hardness	122 R-Scale	ASTM D785

Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	290 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	288 °F	ASTM D648
Vicat Softening Temperature	300 °F	ASTM D1525
CLTE - Flow	1.5E-5 in/in/°F	ASTM E831

Flammability	Nominal Value Unit	Test Method
0.06 in	V2	UL94 TVT Internal/z
0.12 in	V0	UL94 TVT Internal/z

Recommended Processing Guidance

- Drying Temperature 230 to 250 °F
- Drying Time 3 to 6 Hours
- Suggested Max Moisture 0.02 %
- Processing Melt Temperature 590 to 640 °F
- Mold Temperature 175 to 240 °F

¹ note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.