



TRIVALENCE

TriVEX™ 62 (U,R)

Headquarters
3001 Maxx Rd
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

Polycarbonate

General Information

Product Description

High flow polycarbonate

FEATURES

- High flow to fill thin wall and long parts
- High Optical Quality

ADDITIONAL FORMULAS

- Added Release "R"
- Additional UV "U"

COLOR

- All
- Transparent

General

Typical Applications	-Appliance, electrical, lawn & garden, automotive, medical
Processing Method	-Injection
Form(s)	-Pellets
Availability	-North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ASTM D792
Melt Flow Rate (300°C/1.2kg)	40-60	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7	%	TVT Internal
Outdoor Suitability (QUV) (12U Grades)	Pass		TVT Internal

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, brk	8000	psi	ASTM D638
Tensile Elongation	>100	%	ASTM D638
Flexural Modulus	340000	psi	ASTM D790
Notched Izod Impact	10	ft-lbs/in	ASTM D256
Rockwell Hardness	118	R-Scale	ASTM D785

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	252	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	248	°F	ASTM D648
Vicat Softening Temperature	282	°F	ASTM D1525
CLTE - Flow	4.5E-5	in/in/°F	ASTM E831

Flammability	Nominal Value	Unit	Test Method
0.06 in		HB	UL94 - TVT Internal

Recommended Processing Guidance

Drying Temperature	230 to 250	°F
Drying Time	3 to 6	Hours
Suggested Max Moisture	0.02	%
Processing Melt Temperature	580 to 610	°F
Mold Temperature	160 to 200	°F

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.