

Headquarters 3001 Maxx Rd Evansville, IN 47711 800.209.2517

# TriLON™ 61CG30E (U,L,HS,N)

trivalencetechnologies.com

## Polyamide Nylon 6

## **General Information**

#### **Product Description**

30% Glass Fiber Reinforced Nylon 6 offered with various additives.

#### **FEATURES**

- -Good Strength -Oil/Solvent Resistant
- -Economy Grade -High Rigidity
- -Excellent Chemical Resistance
- -Gasoline Resistant
- -30% Glass Fiber Reinforced

## **ADDITIONAL FORMULAS**

- -Added Lubricant "L"
- -Additional UV "U"
- -Additonal Heat Stabilizers "HS"
- -Nucleated "N"

#### **COLOR**

-All

-Translucent/Opaque

## General

Typical Applications

-Appliance, automotive, general, pumps, impellers, housings

Processing Method -Injection Form(s) -Pellets

Compliance -RoHS Compliant - TVT

Availability -North America, Europe, Latin America

ASTM / ISO Properties <sup>1</sup>		
Physical	Nominal Value Unit	Test Method
Density	1.36 g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.5 %	ASTM D955
Outdoor Suitability (QUV) ("U" Grades)	Pass	TVT Internal
Mechanical	Nominal Value Unit	Test Method
Tensile Strength, brk	18,500 psi	ASTM D638
Tensile Strain	>2 %	ASTM D638
Flexural Modulus	1000000 psi	ASTM D790
Notched Izod Impact	1.2 ft-lbs/in	ASTM D256
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	380 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	365 °F	ASTM D648
Melting Point	430 °F	TVT Internal
Flammability	Nominal Value Unit	Test Method
0.06 in	НВ	UL94 - TVT Interna

## **Recommended Processing Guidance**

Drying Temperature170 to 190 °FDrying Time - DESSICANT3 to 6 HoursSuggested Max Moisture0.2 %Processing Melt Temperature480 to 530 °FMold Temperature130 to 195 °F

<sup>1</sup> Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.