



TRIVALENCE

Headquarters
3001 Maxx Rd
Evansville, IN 47711
800.209.2517

TriLON™ 661BGM35 (U,L,HS,N)

trivalencetechnologies.com

Polyamide Nylon 66

General Information

Product Description

General purpose, 35% Glass/Mineral Reinforced Nylon 66 offered with various additives.

FEATURES

-Good Strength -Oil/Solvent Resistant
-Fast Cyling -Low Warp
-Excellent Chemical Resistance
-Gasoline Resistant
-35% Glass/Mineral Reinforced

ADDITIONAL FORMULAS

-Added Lubricant "L"
-Additional UV "U"
-Additional Heat Stabilizers "HS"
-Nucleated "N"

COLOR

-All
-Translucent/Opaque

General

Typical Applications -Appliance, automotive, general, pumps, impellers, housings
Processing Method -Injection
Form(s) -Pellets
Compliance -RoHS Compliant - TVT
Availability -North America, Europe, Latin America

ASTM / ISO Properties¹

| Physical | Nominal Value | Unit | Test Method |
|--|---------------|-------------------|---------------------|
| Density | 1.42 | g/cm ³ | ASTM D792 |
| Molding Shrinkage - Flow (3.2mm) | 0.3 to 0.8 | % | TVT Internal |
| Outdoor Suitability (QUV) ("U" Grades) | Pass | | TVT Internal |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength, brk | 18,000 | psi | ASTM D638 |
| Tensile Strain | >2 | % | ASTM D638 |
| Flexural Modulus | 1,000,000 | psi | ASTM D790 |
| Notched Izod Impact | 1 | ft-lbs/in | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0.45 MPa) | 500 | °F | ASTM D648 |
| Deflection Temperature Under Load (1.8 MPa) | 475 | °F | ASTM D648 |
| Melting Point | 504 | °F | TVT Internal |
| Flammability | Nominal Value | Unit | Test Method |
| 0.06 in | HB | | UL94 - TVT Internal |

Recommended Processing Guidance

Drying Temperature 150 to 175 °F
Drying Time - DESSICANT 3 to 6 Hours
Suggested Max Moisture 0.2 %
Processing Melt Temperature 540 to 570 °F
Mold Temperature 140 to 200 °F

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.