



**TRIVALENCE**

Headquarters  
3001 Maxx Rd  
Evansville, IN 47711  
800.209.2517

# TriLON™ 661CG60 (U,L,HS,N) ISO

[trivalencetechnologies.com](http://trivalencetechnologies.com)

## Polyamide Nylon 6

### General Information

#### Product Description

General purpose, 60% Glass Fiber Reinforced Nylon 66 offered with various additives

#### FEATURES

- Superior Strength -Oil/Solvent Resistant
- Fast Cyling -High Rigidity
- Excellent Chemical Resistance
- Gasoline Resistant
- 60% Glass Fiber Reinforced

#### ADDITIONAL FORMULAS

- Added Lubricant "L"
- Additional UV "U"
- Additonal Heat Stabilizers "HS"
- Nucleated "N"

#### COLOR

- Black Only

#### General

- Typical Applications** -Appliance, automotive, general, pumps, impellers, housings
- Processing Method** -Injection
- Form(s)** -Pellets
- Compliance** -RoHS Compliant - TVT
- Availability** -North America, Europe, Latin America

### ASTM / ISO Properties<sup>1</sup>

	Nominal Value Unit	Test Method
<b>Physical</b>		
Density	1.77 g/cm <sup>3</sup>	ISO 1183A
Molding Shrinkage - Flow (3.2mm)	0.1 to 0.2 %	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass	TVT Internal
<b>Mechanical</b>		
Tensile Strength, brk	260 MPa	ISO 527
Tensile Strain,brk	>1.8 %	ISO 527
Flexural Modulus	22000 MPa	ISO 178
Charpy Notched 23°C	20 kj/m <sup>2</sup>	ISO 179
<b>Thermal</b>		
Deflection Temperature Under Load (1.8 MPa)	230 °C	ISO 75
Melting Point	262 °C	TVT Internal
<b>Flammability</b>		
0.06 in	HB	UL94 - TVT Internal

### Recommended Processing Guidance

- Drying Temperature 150 to 175 °F
- Drying Time - DESSICANT 3 to 6 Hours
- Suggested Max Moisture 0.2 %
- Processing Melt Temperature 540 to 570 °F
- Mold Temperature 140 to 200 °F

<sup>1</sup> Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.