



TRIVALENCE

Headquarters
3001 Maxx Rd
Evansville, IN 47711
800.209.2517

TriLON™ 662BG35 (U,L,HS,N) ISO

trivalencetechnologies.com

Polyamide Nylon 66

General Information

Product Description

35% Glass Fiber Reinforced Nylon 66 offered with various additives. High Strength

FEATURES

- Good Toughness
- Fast Cyling
- High Strength
- Gasoline Resistant
- 35% Glass Fiber Reinforced
- Oil/Solvent Resistant
- High Heat Resistance
- Excellent Chemical Resistance

ADDITIONAL FORMULAS

- Added Lubricant "L"
- Additional UV "U"
- Additional Heat Stabilizers "HS"
- Nucleated "N"

COLOR

- All
- Translucent/Opaque

General

- Typical Applications** -Appliance, transportation, pumps, impellers, housings, gears
- Processing Method** -Injection
- Form(s)** -Pellets
- Compliance** -RoHS Compliant - TVT
- Availability** -North America, Europe, Latin America

ASTM / ISO Properties¹

| Physical | Nominal Value | Unit | Test Method |
|---|---------------|-------------------|---------------------|
| Density | 1.41 | g/cm ³ | ISO 1183 |
| Molding Shrinkage - Flow (3.2mm) | 0.2 to 0.6 | % | ISO 294 |
| Outdoor Suitability (QUV) ("U" Grades) | Pass | | TVT Internal |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength, yld | 205 | MPa | ISO 527 |
| Tensile Strain | >2 | % | ISO 527 |
| Flexural Modulus | 9400 | MPa | ISO 178 |
| Notched Izod Impact | 14 | kJ/m ² | ISO 180 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa) | 250 | °C | ISO 75 |
| Melting Temperature | 262 | °C | ISO 3146 |
| Flammability | Nominal Value | Unit | Test Method |
| 0.06 in | HB | | UL94 - TVT Internal |

Recommended Processing Guidance

- Drying Temperature 70 to 90 °C
- Drying Time - DESSICANT 3 to 6 Hours
- Suggested Max Moisture 0.2 %
- Processing Melt Temperature 285 to 305 °C
- Mold Temperature 80 to 100 °C

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.