



TRIVALENCE

TriLON™ 663MS2 (U,L,HS,N)

Headquarters
3001 Maxx Rd
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

Polyamide Nylon 66

General Information

Product Description

General purpose, Nylon 66 Impact Modified

FEATURES

- Great Impact
- Fast Cyling
- Excellent Chemical Resistance
- Gasoline Resistant
- Oil/Solvent Resistant
- Molybdenum Disulfide

ADDITIONAL FORMULAS

- Added Lubricant "L"
- Additional UV "U"
- Additional Heat Stabilizers "HS"
- Nucleated "N"

COLOR

- All
- Translucent/Opaque

General

- Typical Applications** -Appliance, automotive, general
- Processing Method** -Injection
- Form(s)** -Pellets
- Compliance** -RoHS Compliant - TVT
- Availability** -North America, Europe, Latin America

ASTM / ISO Properties¹

	Nominal Value Unit	Test Method
Physical		
Density	1.12 g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.2mm)	1.2 to 1.6 %	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass	TVT Internal
Mechanical		
Tensile Strength, yld	10,500 psi	ASTM D638
Tensile Strain	>40 %	ASTM D638
Flexural Modulus	270,000 psi	ASTM D790
Notched Izod Impact	6.0 ft-lbs/in	ASTM D256
Thermal		
Deflection Temperature Under Load (1.8 MPa)	180 °F	ASTM D648
Melting Point	504 °F	TVT Internal
Flammability		
0.06 in	HB	UL94 - TVT Internal

Recommended Processing Guidance

- Drying Temperature 150 to 175 °F
- Drying Time - DESSICANT 3 to 6 Hours
- Suggested Max Moisture 0.2 %
- Processing Melt Temperature 540 to 570 °F
- Mold Temperature 140 to 200 °F

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.