

Headquarters 3001 Maxx Rd Evansville, IN 47711 800.209.2517

TriVAN™ 22P (U, R, UR)

trivalenctechnologies.com

Acrylonitrile Butadiene Styrene

General Information

Product Description

Medium flow ABS used in most painting and plating applications.

FEATURES ADDITIONAL FORMULAS COLOR

-Great Impact -Plateable -Added Release "R" -All
-Medium Flow -Additional UV "U" -Opaque

-Weldable

-Paintable

General

Typical Applications -Appliance, electrical, lawn & garden, automotive, medical, lighting, rails

Processing Method -Injection/Extrusion

Form(s) -Pellets

Availability -North America, Europe, Latin America

ASTM / ISO Properties ¹		
Physical	Nominal Value Unit	Test Method
Density	1.04 g/cm ³	ASTM D792
Melt Flow Rate (230°C/3.8kg)	4 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.4 to 0.6 %	TVT Internal
Outdoor Suitability (QUV) (23PU Grades)	Pass	TVT Internal
Mechanical	Nominal Value Unit	Test Method
Tensile Strength, yld	6800 psi	ASTM D638
Tensile Elongation	>18 %	ASTM D638
Flexural Modulus	345000 psi	ASTM D790
Notched Izod Impact	4.2 ft-lbs/in	ASTM D256
Rockwell Hardness	106 R-Scale	ASTM D785
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	188 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	168 °F	ASTM D648
Vicat Softening Temperature	206 °F	ASTM D1525
CLTE - Flow	3.3E-5 in/in/°F	ASTM E831
Flammability	Nominal Value Unit	Test Method
0.06 in	НВ	UL94 - TVT Internal

Recommended Processing Guidance

Drying Temperature175 to 200 °FDrying Time3 to 5 HoursSuggested Max Moisture0.04 %Processing Melt Temperature480 to 530 °FMold Temperature110 to 175 °F

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.