

**TRIVALENCE**

TriVEX™ 12G30 (U,R)

Headquarters
3001 Maxx Rd
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

Polycarbonate

General Information

Product Description

Glass fiber reinforced polycarbonate

FEATURES

- 30% Glass Fiber Reinforced
- Good Strength
- Good Creep Resistance
- Low Flow

ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"

COLOR

-All

General

Typical Applications

-Appliance, electrical, lawn & garden, automotive, electronic

Processing Method

-Injection

Form(s)

-Pellets

Availability

-North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

| Physical | Nominal Value Unit | Test Method |
|--|------------------------|--------------------|
| Density | 1.43 g/cm ³ | ASTM D792 |
| Melt Flow Rate (300°C/1.2kg) | 8 g/10min | ASTM D1238 |
| Molding Shrinkage - Flow (3.2mm) | 0.2 to 0.4 % | TVT Internal |
| Outdoor Suitability - QUV ("U" grades only) | Pass | QUV - TVT Internal |
| Mechanical | Nominal Value Unit | Test Method |
| Tensile Strength, yld | 17,000 psi | ASTM D638 |
| Tensile Elongation | >3 % | ASTM D638 |
| Flexural Modulus | 1000000 psi | ASTM D790 |
| Notched Izod Impact | 1.5 ft-lbs/in | ASTM D256 |
| Rockwell Hardness | 123 R-Scale | ASTM D785 |
| Thermal | Nominal Value Unit | Test Method |
| Deflection Temperature Under Load (0.45 MPa) | 285 °F | ASTM D648 |
| Deflection Temperature Under Load (1.8 MPa) | 275 °F | ASTM D648 |
| Vicat Softening Temperature | 290 °F | ASTM D1525 |
| CLTE - Flow | 1.7E-5 in/in/°F | ASTM E831 |
| Flammability | Nominal Value Unit | Test Method |
| 0.06 in | HB | UL94 TVT Internal |

Recommended Processing Guidance

| | |
|-----------------------------|---------------|
| Drying Temperature | 230 to 260 °F |
| Drying Time | 3 to 6 Hours |
| Suggested Max Moisture | 0.02 % |
| Processing Melt Temperature | 560 to 600 °F |
| Mold Temperature | 175 to 230 °F |

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.