

**TRIVALENCE**

TriVEX™ 12G30FR0

Headquarters
3001 Maxx Rd
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

Polycarbonate

General Information

Product Description

Flame retardant, 30% glass reinforced product

FEATURES

- Flame Retardant
- Great Impact
- UV Stabilized
- Low Flow

ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"
- Additional Melt Flows

COLOR

-All

General

Typical Applications

-Appliance, electrical, lawn & garden, automotive, electronic

Processing Method

-Injection/Extrusion

Form(s)

-Pellets

Availability

-North America, Europe, Asia, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value Unit	Test Method
Density	1.43 g/cm ³	ASTM D792
Melt Flow Rate (300°C/1.2kg)	6 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.4 %	TVT Internal
Outdoor Suitability (QUV) ("U" grades)	Pass	TVT Internal QUV
Mechanical	Nominal Value Unit	Test Method
Tensile Strength, yld	14000 psi	ASTM D638
Tensile Elongation	2 %	ASTM D638
Flexural Modulus	950,000 psi	ASTM D790
Notched Izod Impact	1.4 ft-lbs/in	ASTM D256
Rockwell Hardness	122 R-Scale	ASTM D785
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	305 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	298 °F	ASTM D648
Flammability	Nominal Value Unit	Test Method
0.06 in	V0	UL94 TVT Internal
0.12 in	V0/5VA	UL94 TVT Internal

Recommended Processing Guidance

Drying Temperature	230 to 250 °F
Drying Time	3 to 6 Hours
Suggested Max Moisture	0.02 %
Processing Melt Temperature	580 to 615 °F
Mold Temperature	175 to 230 °F

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.