

**TRIVALENCE**

# TriVEX™ 21G30FR0 (6M)

Headquarters  
3001 Maxx Rd  
Evansville, IN 47711  
800.209.2517

[trivalencetechnologies.com](http://trivalencetechnologies.com)

## Polycarbonate

### General Information

#### Product Description

Flame resistant, 30% glass reinforced product

#### FEATURES

- Flame Resistant
- Great Impact
- UV Stabilized
- Low Flow

#### ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"
- Additional Melt Flows

#### COLOR

-All

#### General

##### Typical Applications

-Appliance, electrical, lawn & garden, automotive, electronic

##### Processing Method

-Injection/Extrusion

##### Form(s)

-Pellets

##### Availability

-North America, Europe, Asia, Latin America

### ASTM / ISO Properties<sup>1</sup>

Physical	Nominal Value Unit	Test Method
Density	1.43 g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (300°C/1.2kg)	6 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.4 %	TVT Internal
Outdoor Suitability (QUV) ("U" grades)	Pass	TVT Internal QUV
Mechanical	Nominal Value Unit	Test Method
Tensile Strength, yld	14000 psi	ASTM D638
Tensile Elongation	2 %	ASTM D638
Flexural Modulus	950,000 psi	ASTM D790
Notched Izod Impact	1.4 ft-lbs/in	ASTM D256
Rockwell Hardness	122 R-Scale	ASTM D785
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	305 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	298 °F	ASTM D648
Flammability	Nominal Value Unit	Test Method
0.06 in	V0	UL94 TVT Internal
0.12 in	V0/5VA	UL94 TVT Internal

#### Recommended Processing Guidance

Drying Temperature	230 to 250 °F
Drying Time	3 to 6 Hours
Suggested Max Moisture	0.02 %
Processing Melt Temperature	580 to 615 °F
Mold Temperature	175 to 230 °F

<sup>1</sup> Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.