



TRIVALENCE

TriVEX™ 22FR2 (20M)

Polycarbonate

Headquarters
3001 Maxx Rd
Evansville, IN 47711
800.209.2517

trivalencetechnologies.com

General Information

Product Description

UL 94V2, Polycarbonate, high flow, flame retardant, UL Listed, V2 rated, UV, release added, weatherable.

FEATURES

- Flame Retardant
- High Flow
- High Impact
- UV Stabilized
- Weatherable

ADDITIONAL FORMULAS

- Added Release "R"

COLOR

- All



**Underwriters
Laboratories**

General

| | |
|-----------------------------|---|
| Typical Applications | -Appliance, electrical, lawn & garden, automotive |
| Processing Method | -Injection |
| Form(s) | -Pellets |
| Availability | -North America, Europe, Asia, Latin America |

ASTM / ISO Properties¹

| Physical | Nominal Value | Unit | Test Method |
|--|---------------|-------------------|-------------------|
| Density | 1.20 | g/cm ³ | ASTM D792 |
| Melt Flow Rate (300°C/1.2kg) | 20 | g/10min | ASTM D1238 |
| Molding Shrinkage - Flow (3.2mm) | 0.5 to 0.7 | % | TVT Internal |
| Outdoor Suitability (QUV) | Pass | | TVT Internal |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength, brk | 9200 | psi | ASTM D638 |
| Tensile Elongation | >100 | % | ASTM D638 |
| Flexural Modulus | 320000 | psi | ASTM D790 |
| Notched Izod Impact | 12 | ft-lbs/in | ASTM D256 |
| Rockwell Hardness | 118 | R-Scale | ASTM D785 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0.45 MPa) | 278 | °F | ASTM D648 |
| Deflection Temperature Under Load (1.8 MPa) | 270 | °F | ASTM D648 |
| Vicat Softening Temperature | 308 | °F | ASTM D1525 |
| RTI Elec | 176 | °F | UL 746 |
| RTI IMP | 176 | °F | UL 746 |
| RTI Str | 176 | °F | UL 746 |
| CLTE - Flow | 3.8E-5 | in/in/°F | ASTM E831 |
| Flammability | Nominal Value | Unit | Test Method |
| 0.06 in | V2 | | UL94 File E494706 |
| 0.12 in | V2 | | UL94 File E494706 |

Recommended Processing Guidance

| | |
|-----------------------------|---------------|
| Drying Temperature | 230 to 250 °F |
| Drying Time | 3 to 6 Hours |
| Suggested Max Moisture | 0.02 % |
| Processing Melt Temperature | 520 to 560 °F |
| Mold Temperature | 140 to 180 °F |

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.