



TRIVALENCE

Headquarters
3001 Maxx Rd
Evansville, IN 47711
800.209.2517

TriVEX™ 23FR5 (24M)¹ E494706 UL Pending

trivalencetechnologies.com

Polycarbonate

General Information

Product Description

UL certified flame resistant product is available in melt flow ranges of 8 - 24.

FEATURES

- Flame Resistant -Elevated RTI
- Great Impact -High Flow
- UV Stabilized
- f1

ADDITIONAL FORMULAS

- Added Release
- Additional Melt Flows

COLOR

- All



**Underwriters
Laboratories**

General

- | | |
|-----------------------------|---|
| Typical Applications | -Appliance, electrical, lawn & garden, automotive |
| Processing Method | -Injection |
| Form(s) | -Pellets |
| Availability | -North America, Europe, Asia, Latin America |

ASTM / ISO Properties¹

Physical

	Nominal Value Unit	Test Method
Density	1.21 g/cm ³	ASTM D792
Melt Flow Rate (300°C/1.2kg)	24 g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7 %	TVT Internal
Outdoor Suitability (QUV)	f1	UL 746C Pending

Mechanical

	Nominal Value Unit	Test Method
Tensile Strength, brk	9200 psi	ASTM D638
Tensile Elongation	>100 %	ASTM D638
Flexural Modulus	320000 psi	ASTM D790
Notched Izod Impact	12 ft-lbs/in	ASTM D256
Rockwell Hardness	118 R-Scale	ASTM D785

Thermal

	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	278 °F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	270 °F	ASTM D648
Vicat Softening Temperature	308 °F	ASTM D1525
RTI Elec	239 °F	UL 746B Pending
RTI IMP	239 °F	UL 746B Pending
RTI Str	239 °F	UL 746B Pending
CLTE - Flow	3.8E-5 in/in/°F	ASTM E831

Flammability

	Nominal Value Unit	Test Method
0.06 in	V0	UL94 File E494706
0.10 in	V0, 5VA	UL94 File E494706

Recommended Processing Guidance

	Nominal Value Unit
Drying Temperature	230 to 250 °F
Drying Time	3 to 6 Hours
Suggested Max Moisture	0.02 %
Processing Melt Temperature	520 to 560 °F
Mold Temperature	140 to 180 °F

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.