



TRIVALENCE

Headquarters
3001 Maxx Road
Evansville, IN 47711
800.209.2517

TriVAN™ 12G15 (U, R, UR)

trivalencetechnologies.com

Acrylonitrile Butadiene Styrene Glass Fiber Reinforced

General Information

Product Description

Acrylonitrile Butadiene Styrene 15% Glass Fiber reinforced, Impact Modified

FEATURES

- Good Impact
- Medium Flow
- Good Stiffness

ADDITIONAL FORMULAS

- Added Release "R"
- Additional UV "U"

COLOR

- All
- Opaque

General

Typical Applications

-Appliance, construction

Processing Method

-Injection/Extrusion

Form(s)

-Pellets

Availability

-North America, Europe, Latin America

ASTM / ISO Properties¹

	Nominal Value	Unit	Test Method
Physical			
Density	1.14	g/cm ³	ASTM D792
Melt Flow Rate (230°C/3.8kg)	2	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.1 to 0.3	%	TVT Internal
Outdoor Suitability (QUV) ("U" Grades)	Pass		TVT Internal
Mechanical			
Tensile Strength, yld	10200	psi	ASTM D638
Tensile Elongation	>2.5	%	ASTM D638
Flexural Modulus	660000	psi	ASTM D790
Notched Izod Impact	2	ft-lbs/in	ASTM D256
Thermal			
Deflection Temperature Under Load (0.45 MPa)	218	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)	212	°F	ASTM D648
Vicat Softening Temperature	218	°F	ASTM D1525
Flammability			
0.06 in	HB		UL94 - TVT Internal

Recommended Processing Guidance

Drying Temperature	175 to 200	°F
Drying Time	3 to 5	Hours
Suggested Max Moisture	0.04	%
Processing Melt Temperature	480 to 530	°F
Mold Temperature	110 to 175	°F

1

Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.