



Headquarters
3001 Maxx Road
Evansville, IN 47711
800.209.2517

TriVAN™ 22S (UR)

Acrylonitrile Styrene Acrylate

trivalencetechnologies.com

General Information

Product Description

Medium flow ASA, general purpose

FEATURES

-Great Weatherability
-Medium Flow

ADDITIONAL FORMULAS

-Added Release "R"

COLOR

-All
-Opaque

General

Typical Applications -Lawn & garden, transportation, construction, outdoor
Processing Method -Injection/Extrusion
Form(s) -Pellets
Availability -North America, Europe, Latin America

ASTM / ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Melt Flow Rate (220°C/10.0kg)	12	g/10min	ISO 1133
Molding Shrinkage - Flow (3.2mm)	0.4 to 0.7	%	ISO 294
Outdoor Suitability (QUV)	Pass		TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	45	MPa	ISO 527
Tensile Elongation	>6	%	ISO 527
Flexural Modulus	2200	MPa	ISO 178
Charpy Impact (73F)	15	kJ/m ²	ISO 179A
Rockwell Hardness	100	R-Scale	ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	101	°C	ISO 75
Deflection Temperature Under Load (1.8 MPa)	97	°C	ISO 75
Vicat Softening Temperature	105	°C	ISO 75
CLTE - Flow	8.5E-5	cm/cm/°C	ISO 11359
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 - TVT Internal

Recommended Processing Guidance

Drying Temperature 70 to 90 °C
Drying Time 3 to 5 Hours
Suggested Max Moisture 0.02 %
Processing Melt Temperature 220 to 270 °C
Mold Temperature 40 to 80 °C

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.