



**TRIVALENCE**

Headquarters  
3001 Maxx Road  
Evansville, IN 47711  
800.209.2517

# TriVET™ 11B (U,R)

Polybutylene Terephthalate

trivalancetechnologies.com

## General Information

### Product Description

Low flow, high IV, modified PBT.

#### FEATURES

- 1.20IV
- High Molecular Weight
- Good strength
- Good Chemical Resistance
- Low Flow

#### ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"

#### COLOR

- All

### General

- Typical Applications** -Transportation, housing, electrical
- Processing Method** -Injection/Extrusion
- Form(s)** -Pellets
- Availability** -North America, Europe, Asia, Latin America

## ASTM / ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm <sup>3</sup>	ISO 1183
Melt Flow Rate (250°C/2.16kg)	10	g/10min	ISO 1133
Molding Shrinkage - Flow (3.2mm)	1.8 to 2.0	%	TVT Internal
Outdoor Suitability - QUV ("U" grades only)	Pass		QUV - TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	58	MPa	ISO 527
Tensile Modulus	2500	MPa	ISO 178
Charpy Notched Impact	3.4	kJ/m <sup>2</sup>	ISO 179
Rockwell Hardness	70	M-Scale	ISO 2039
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	301	°F	ISO 75
Deflection Temperature Under Load (1.8 MPa)	122	°F	ISO 75
Vicat Softening Temperature	364	°F	ISO 75
CLTE - Flow	6.1E-5	in/in/°F	ASTM E831
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 TVT Internal

### Recommended Processing Guidance

- Drying Temperature 110 to 130 °C
- Drying Time 3 to 6 Hours
- Suggested Max Moisture 0.02 %
- Processing Melt Temperature 240 to 275 °C
- Mold Temperature 60 to 90 °C

<sup>1</sup> Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.