



**TRIVALENCE**

Headquarters  
3001 Maxx Road  
Evansville, IN 47711  
800.209.2517

# TriVET™ 21B (U,R)

Polybutylene Terephthalate

trivalancetechnologies.com

## General Information

### Product Description

General purpose, unreinforced PBT

#### FEATURES

- Improved processing
- Chemical Resistance
- RoHS/REACH Compliant
- Medium Flow

#### ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"

#### COLOR

-All

### General

#### Typical Applications

-Appliance, electrical, lawn & garden.

#### Processing Method

-Injection/Extrusion

#### Form(s)

-Pellets

#### Availability

-North America, Europe, Latin America

## ASTM / ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (250°C/2.16kg)	60	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.9 to 1.6	%	ASTM D955
Outdoor Suitability - QUV ("U" grades only)	Pass		QUV - TVT Internal
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength, yld	7,200	psi	ASTM D638
Tensile Elongation	>50	%	ASTM D638
Flexural Modulus	330,000	psi	ASTM D790
Notched Izod Impact, 73F	0.9	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)(0.25in)	300	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)(0.25in)	130	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 TVT Internal
Recommended Processing Guidance			
Drying Temperature	220 to 255	°F	
Drying Time	3 to 6	Hours	
Suggested Max Moisture	0.02	%	
Processing Melt Temperature	480 to 500	°F	
Mold Temperature	140 to 190	°F	

<sup>1</sup> Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.