



Headquarters
3001 Maxx Road
Evansville, IN 47711
800.209.2517

TriVET™ 21G10CPE

Proprietary Copolyester

trivalancetechnologies.com

Proprietary Copolyester			General Information	
Product Description				
Glass fiber reinforced proprietary copolyester				
FEATURES		ADDITIONAL FORMULAS		COLOR
-10% Glass Fiber Reinforced		-Added Release "R"		-All
-Chemical Resistance		-Added UV "U"		
-RoHS/REACH Compliant				
-Medium Flow				
General				
Typical Applications		-Appliance, electrical, lawn & garden.		
Processing Method		-Injection/Extrusion		
Form(s)		-Pellets		
Availability		-North America, Europe, Latin America		
ASTM / ISO Properties ¹				
Physical		Nominal Value	Unit	Test Method
Density		1.25	g/cm ³	ASTM D792
Melt Flow Rate (250°C/2.16kg)		5	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)		0.03 to 0.06	%	ASTM D955
Outdoor Suitability - QUV ("U" grades only)		Pass		QUV - TVT Internal
Mechanical		Nominal Value	Unit	Test Method
Tensile Strength, yld		9,700	psi	ASTM D638
Tensile Elongation		>7	%	ASTM D638
Flexural Modulus		390,000	psi	ASTM D790
Notched Izod Impact, 73F		1.2	ft-lb/in	ASTM D256
Thermal		Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)		218	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)		195	°F	ASTM D648
CLTE - Flow		3.1E-5	in/in/°F	ASTM E831
Flammability		Nominal Value	Unit	Test Method
0.06 in		HB		UL94 TVT Internal
Recommended Processing Guidance				
Drying Temperature		180 to 200	°F	
Drying Time		3 to 6	Hours	
Suggested Max Moisture		0.02	%	
Processing Melt Temperature		530 to 540	°F	
Mold Temperature		120 to 170	°F	

¹ Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.