



## TriVET ™21G50BP (U,R)

Polybutylene Terephthalate + PET

trivalencetechnologies.com

COLOR

-All

General Info	ormatio
--------------	---------

**Product Description** 

Glass fiber reinforced polybutylene terephthalate + PET

FEATURES ADDITIONAL FORMULAS

-50% Glass Fiber Reinforced -Added Release "R"
-Great Strength -Added UV "U"

-Good Dimensional Stability

-Low Flow

General

Typical Applications -Appliance, electrical, lawn & garden, automotive, electronic

Processing Method -Injection
Form(s) -Pellets

Availability -North America, Europe, Asia, Latin America

ASTM / ISO Properties¹		
Physical	Nominal Value Unit	Test Method
Density	1.73 g/cm <sup>3</sup>	ISO 1183
Melt Flow Rate (275°C/2.16kg)	12 g/10min	ISO 1133
Molding Shrinkage - Flow (3.2mm)	0.2 to 0.4 %	TVT Internal
Outdoor Suitability - QUV ("U" grades only)	Pass	QUV - TVT Internal
Mechanical	Nominal Value Unit	Test Method
Tensile Strength, yld	165 MPa	ISO 527
Tensile Elongation	>1.5 %	ISO 527
Flexural Modulus	17,000 MPa	ISO 178
Charpy Notched Impact	10.0 kJ/m2	ISO 179
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)	220 °C	ISO 75
Deflection Temperature Under Load (1.8 MPa)	205 °C	ISO 75
Vicat Softening Temperature	215 °C	ISO 75
Flammability	Nominal Value Unit	Test Method
0.06 in	НВ	UL94 TVT Internal

## Recommended Processing Guidance

 Drying Temperature
 110 to 130 °C

 Drying Time
 3 to 6 Hours

 Suggested Max Moisture
 0.02 %

 Processing Melt Temperature
 250 to 280 °C

 Mold Temperature
 60 to 100 °C

Note: The values listed on this guide are typical values based on general molding conditions and used solely for the purpose of general material processing. It is recommended that application properties be derived from actual molded articles, whereas properties as molded could vary. These are not to be used as specifications. This data does not provide an implied conditional warranty.